

LAM

Material designation		Chemical composition*			
CuZn40Pb2		Elements	% mean	Impurities	% max.
		Cu	58.4	Fe	0.07
		Pb	2	Sn	0,20
EN 12164 / EN 12165 / EN 12167				Ni	0.03
CW617N				Mn	0.1
				Al	0.05
		Zn	balance	Other	0.2

* Reference values in % by weight

Properties and typical applications
Free cutting and hot forging brass. It has a low iron content which can be useful for making non-magnetic parts. This alloy is used in many fields such as architecture, plumbing or general engineering.

Physical properties at 20°C		Heat treatment	
Density (g/cm ³)	8.4	Melting range (°C)	890-900
Young modulus (GPa)	103	Hot working (°C)	650-800
Thermal expansion coefficient (20-300°C) (10 ⁻⁶ /K)	21	Annealing temperature (°C)*	450-600
Thermal conductivity (W/m.K)	120	Stress relieving treatment (°C)**	250-350
Thermal capacity (J/Kg.K)	377	<i>* Annealing treatment of a material leads to reduce its hardness and increase its ductility.</i>	
Electrical conductivity (% I.A.C.S.)	26	<i>** Stress relieving treatment allows to eliminate the residual stresses present in the material in order to avoid the stress corrosion cracking.</i>	

Forming		Joining	
Hot forming	Excellent	Soldering	
Cold forming	Fair	Soft	Excellent
Machinability	90% (Ref: CuZn39Pb3 = 100%)	Hard	Good
Corrosion resistance		Welding	
Free-cutting brasses generally have good resistance to corrosion in organic materials and neutral or alkaline compounds. However, they may present a problem of cracking corrosion in an aggressive environment in the presence of internal stresses, but also a risk of dezincification in the presence of hot and acidic water.		Gaz welding	Not recommended
		Inert gas shielded arc welding	Not recommended
		Resistance welding	Not recommended

Mechanical properties according to EN12164						
Condition of material	Diameter [mm]		Rp0,2 [Mpa] min. or max.	Rm [Mpa] min.	A(%) min.	Hardness HB
	from	to				
M	All		As extruded - without specific mechanical properties			
R360	6	80	< 350	360	20	-
H090			-	-	-	90-125
R430	6	40	> 220	430	10	-
H110			-	-	-	110-160
R500	6	14	> 350	500	5	-
H135			-	-	-	> 135

Fabrication range	
Available forms:	   
Do not hesitate to contact us for further information regarding the dimensions, tolerances and metallurgical conditions. Our technical teams are by your side to help you succeed in your projects.	
info@m-lego.com	