

Pb < 0,1% 0% Cadmium RoHS & ELV ok

CS 60001 72401 LA FERTE BERNARD cedex

France

Tél: +33 (0)2 43 60 60 65 Fax: +33 (0)2 43 93 55 03

info@m-lego.com

- High tensile lead free brass -

BL₆

Material designati	on	CI	hemical compos	ition*	
CuZn23AI4		Elements	% mean	Impurities	% max.
		Cu	66	Pb	0.1
		Al	4.3		
NFL 14-708	CuZn23Al4	Fe	2	Other	0.4
		Mn	2.8		
		Ni	1		
		Zn	balance		

^{*} Reference values in % by weight

Properties and typical applications

This alloy presents an excellent mechanical and wear resistance. It is especially known for its good resistance to friction under heavy loads. CuZn23Al4 is used in aerospace, shipbuilding, water industry, screws & bolts...

Physical properties at 20°C		Heat treatment	
Density (g/cm3)	7.8	Melting range (°C)	880-900
Young modulus (GPa)	103	Hot working (°C)	670-750
Thermal expansion coefficient (20-300°C) (10 ⁻⁶ /K)	17	Annealing temperature (°C)*	500-600
Thermal conductivity (W/m.K)	38	Stress relieving treatment (°C)**	300-400
Thermal capacity (J/Kg.K)	380	* Annealing treatment of a material leads to	reduce its
Electrical conductivity (% I.A.C.S.)	13	hardness and increase its ductility.	
		** Stress relieving treatment allows to aliminate	the recidual

^{**} Stress relieving treatment allows to eliminate the residual stresses present in the material in ordrer to avoid the stress corrosion cracking.

Forming		Joining		
Hot forming	Excellent	Soldering		
Cold forming	Fair	Soft	Not recommanded	
Machinability	55% (CuZn39Pb3 = 100%)	Hard	Not recommanded	
Corrosion resistance		Welding		
High tensile brasses generally exhibit good corrosion resistance to organic materials and neutral or alkaline compounds due to alloying elements.		Gaz welding	Fair	
		Inert gas shielded arc welding	Not recommanded	
		Resistance welding	Not recommanded	

Mechanical properties according to NFL 14-108				
Condition of material	Rp0,2 [Mpa]	Rm [Mpa]	A(%)	Hardness HB
	min.	min.	min.	min.
As extruded with or without heat	270	590	15	170

Fabrication range

Available forms:









Do not hesitate to contact us for further information regarding the dimensions, tolerances and metallurgical conditions. Our technical teams are by your side to help you succeed in your projects.

info@m-lego.com