

CS 60001 72401 LA FERTE BERNARD cedex

France

Tél: +33 (0)2 43 60 60 65 Fax: +33 (0)2 43 93 55 03

info@m-lego.com

## **CW722R**

## - High Tensile Brass -

BL8

Material designation		Chemical composition*			
		Elements	% mean	Impurities	% max.
CuZn40Mn1Pb1FeSn		Cu	57.1	Ni	0.2
		Pb	1.25		
EN 12164 / 12165 / 12167	CW722R	Mn	1.5	Other	0.3
BS 2872 - 2874	CZ115	Sn	0.5		
NF A 51 - 106	CuZn - classe 1	Fe	0.8		
		Zn	balance		

<sup>\*</sup> Reference values in % by weight

## Properties and typical applications

High tensile brass for machining and hot working. It is used in valves and gas fittings, automotive equipment, pump fittings, electrical connectors

Physical properties at 20°C	Heat treatment		
Density (g/cm3)	8.3	Melting range (°C)	890-910
Young modulus (GPa)	97	Hot working (°C)	650-700
Thermal expansion coefficient (20-300°C) (10 <sup>-6</sup> /K)	20	Annealing temperature (°C)*	450-550
Thermal conductivity (W/m.K)	88	Stress relieving treatment (°C)**	300-400
Thermal capacity (J/Kg.K)	380	* Annealing treatment of a material leads t	o reduce its
Electrical conductivity (% I.A.C.S.)	18	hardness and increase its ductility.	

<sup>\*\*</sup> Stress relieving treatment allows to eliminate the residual stresses present in the material in ordrer to avoid the stress corrosion cracking.

Forming		Joining		
Hot forming	Very good	Soldering		
Cold forming	Fair	Soft	Good	
Machinability	80% (CuZn39Pb3 = 100%)	Hard	Good	
Corrosion resistance		Welding		
Special brass alloys show in general a good corrosion resistance in neutral, alkaline and organic fluids due to alloying		Gaz welding	Not recommanded	
		Inert gas shielded arc welding	Not recommanded	
elements.		Resistance welding	Not recommanded	

Mechanical properties according to EN12164							
Condition	Diameter [mm]		Rp0,2 [Mpa]	Rm [Mpa]	A(%)	Hardness HB	
of material	from	to	min.	min.	min.	naturess no	
M	All A		As extr	extruded - without specific mechanical properties			
R440	40	40	80	180	440	20	-
H100		00	-	-	-	100-140	
R500	<b>R500</b> 6	40	270	500	12	-	
H130		40	-	-	-	> 130	

## Fabrication range

Available forms:









Do not hesitate to contact us for further information regarding the dimensions, tolerances and metallurgical conditions. Our technical teams are by your side to help you succeed in your projects.

info@m-lego.com