

CS 60001 72401 LA FERTE BERNARD cedex France Tél : +33 (0)2 43 60 60 65 Fax : +33 (0)2 43 93 55 03 info@m-lego.com

D10

Material desig	gnation	CI	nemical compo	sition*	
		Elements	% mean	Impurities	% max.
CuAl10Ni5Fe4		Fe	3.8	Pb	0.02
		Ni	4.9	Sn	0.10
NF A 51-116	CuAl10Ni5Fe4	Mn	0.7	Si	0.10
NF L 14-705	CuAl10Ni5Fe4	AI	10.0	Zn	0.30
ASTM B150	C63000				
AMS 4640 F	C63000	Cu	Balance	Others	0.50
EN 12163 / 12165 / 12167	CW307G	* Reference values	* Reference values in % by weight		
DIN 17665	CuAl10Ni5Fe4				

Properties and typical applications This alloy is ideal for applications in severe conditions of friction, mechanical loading and corrosion. D10 is widely used in marine and aerospace applications.

Physical properties at 20°C		Heat treatment		
Density (g/cm3)	7.6	Melting range (°C)	1050-1075	
Young modulus (GPa)	127	Hot working (°C)	850-950	
Thermal expansion coefficient (20-300°C) (10 ⁻⁶ /K)	17	Annealing temperature (°C)*	650-750	
Thermal conductivity (W/m.K)	39	Stress relieving treatment (°C)**	300-400	
Thermal capacity (J/Kg.K)	419	* Annealing treatment of a material leads to reduce hardness and increase its ductility.		
Electrical conductivity (% I.A.C.S.)	7			
		** Stress relieving treatment allows to eliminate stresses present in the material in ordrer to avo corrosion cracking.	the residual and the stress	

	Forming	Joining		
Hot forming	Good	Soldering		
Cold forming	Not recommanded	Soft	Not recommanded	
Machinability	40% (CuZn39Pb3 = 100%)	Hard	Fair	
Corrosion resistance		Welding		
The bronzes of aluminum have a high corrosion resistance, in particular in the sea environments.		Gaz welding	Not recommanded	
		Inert gas shielded arc welding	Good	
		Resistance welding	Good	

	Mechanical properties according to EN 12163						
Condition	Diameter [mm]		Rp0,2 [Mpa]	Rm [Mpa]	A(%)	Hardness HB	
of material	from	to	min.	min.	min.		
М	All		As extruded - without specific mechanical properties				
R680	8	8	80	320	680	10	-
H170			00	-	-	-	170-210
R740	R740 H200	80	400	740	8	-	
H200		00	-	-	-	> 200	

Fabrication range

Available forms:

Do not hesitate to contact us for further information regarding the dimensions, tolerances and metallurgical conditions. Our technical teams are by your side to help you succeed in your projects.

info@m-lego.com

Non contractual document - Information given as an indication